

FIREFLY PLUS 60

TECHNICAL DATA SHEET

DESCRIPTION

Composite Cavity Fire Barrier.
Combined integrity and insulation.
Suitable for vertical and horizontal applications

WEIGHT

2.2kg/m² nominal

THICKNESS

10 mm nominal

BS 476 PART 6
FIRE PROPAGATION TEST
WIRA Testing Centre

Fire Propagation Index 2.56

BS 476 PART 7
SURFACE SPREAD OF FLAME
WIRA Testing Centre

Certification to "Class 1" pass

BS 476 CLASS "0" BUILDING REGULATIONS
WIRA Testing Centre

Complies with requirements

BS 476 PART 20/22 1987 CLAUSE 5
Faverdale Technology Centre &
Tested and Assessed at Loss Prevention Council

INTEGRITY: 60 minutes
INSULATION: 38 minutes

BS 476 PART 20/22 1987 - HORIZONTAL
Tested and Assessed at Loss Prevention Council

INTEGRITY: 60 minutes
INSULATION: 38 minutes

BS 476 PART 20: 1987/PREN 1366-3: 1993
PENETRATION SYSTEM
Warrington Fire Research

INTEGRITY: 60 minutes

SOUND REDUCTION INDEX IN ACCORDANCE WITH
THE PRINCIPALS OF BS EN ISO 140/III 1995
The University of Salford

16 dB

**FIREFLY PLUS 60 satisfies the requirements of the Building Regulations 1991 (1992 edition)
Approved Document B, paragraph 9.6 and Appendix A, table A1, item 16.**

PACK SIZES

LENGTH: 6 metres nominal
WIDTH: 130 cms nominal
WEIGHT: 17.16 Kg nominal

18/0800

FIREFLY PLUS 60 to be fitted in accordance with manufacturer guidelines.

ECO

TBA
TEXTILES

TBA TEXTILES LTD
P.O. Box 40
Rochdale, Lancashire
OL12 7EQ
England

Int. Tel: +44 1706 647422
Dir. Tel: 01706 758817
Int. Fax: +44 1706 750256
website: www.tbafirefly.com

e.mail: ecoelho@tbatextiles.co.uk / vfisher@tbatextiles.co.uk



LPCB Ref. No. 3571/02
Approved to BS476: Part 22: 1987



INVESTOR IN PEOPLE

Q1784